



Technical Data Sheet

Product	TM89x SheenSeries		
Description	Clear polyurethane self sealers		
Color	Clear		
Woods / Substrates for which the product is suitable	Light color hardwood		
	Dark color hardwood		
	Exotic wood		
Chemical-physical Properties			
CODE	Density (Kg/l)	Density (lb/US gal)	Solid content %
TM892	0,987 ± 0,030	8,2 ± 0,3	47,2 ± 2
TM893	0,993 ± 0,030	8,3 ± 0,3	47,9 ± 2
TM896	1,009 ± 0,030	8,4 ± 0,3	49,4 ± 2
TM897	1,020 ± 0,030	8,5 ± 0,3	50,3 ± 2
(series average values)	Viscosity (EN ISO 2431) ISO 6 cup		77 ± 5
	Viscosity (Ford 6 cup)		26 ± 2
USAGE INDICATIONS			
Additional products		Quantities	
Hardener	TXS518	In weight w/w %	50
		In volume v/v %	52,7
		Solid content %	26,2 ± 2
Thinner	TZ3648	In weight w/w %	30
		In volume v/v %	35
READY TO USE PRODUCT PROPERTIES (AVERAGE)			
	Solid content 1st + 2nd component (%)	40,2 ± 2	
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)	4 h	
	Viscosity (EN ISO 2431) ISO 4 cup	36 ± 3	
	Viscosity (Ford 4 cup)	15 ± 2	
Code/Sheen	CODE	Sheen level EN ISO 2813 (angle measurement 60°)	
		applied micron:	150
		Wet Mils:	5,9
	TM892	Sheen	50 ± 3
	TM893	Sheen	25 ± 2
	TM896	Sheen	10 ± 1
TM897	Sheen	5 ± 1	



Application		Quantities			
Curtain coater		gr/m ² min-max:	120	-	150
		Wet Mills min-max	5,0	-	6,2
Hand spray		gr/m ² min-max:	130	-	150
		Wet Mills min-max	5,4	-	6,2
Manual roller		gr/m ² min-max:	80	-	100
		Wet Mills min-max	3,3	-	4,1
PRODUCT PROPERTIES AFTER APPLICATION					
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying		12 h		
	Dust free		15 min		
	Touch dry		25 min		
	Hard dry		12 h		
	Sandable after (time)		4 h		
	Maximum time between layers without sanding		2-3 h		
	Hot air drying		(Time and temperature according to the drying system in use)		
Additional products		Quantities			
Properties	Excellent Drying speed				
Hardener	TX72	In weight w/w %	50		
		In volume v/v %	50,5		
	Solid content %	25,0	±	2	
Thinner	TZ3648	In weight w/w %	10		
		In volume v/v %	12		
READY TO USE PRODUCT PROPERTIES (AVERAGE)					
	Solid content 1st + 2nd component (%)		39,8 ± 2		
	Pot-Life - mixture (maximum pot-life of the product prepared according to usage indications)		1 h		
	Viscosity (EN ISO 2431) ISO 4 cup		47 ± 4		
	Viscosity (Ford 4 cup)		17 ± 2		
Code/Sheen	CODE		Sheen level EN ISO 2813 (angle measurement 60°)		
			applied micron: 150		
			Wet Mills: 5,9		
	TM892		Sheen	50 ±	3
	TM893		Sheen	30 ±	2
	TM896		Sheen	10 ±	1
TM897		Sheen	5 ±	1	



Application	Quantities	
	Curtain coater	gr/m ² min-max: 120 - 150
Hand spray	gr/m ² min-max: 130 - 150	Wet Mills min-max 5,2 - 6,1
	Manual roller	gr/m ² min-max: 80 - 100
PRODUCT PROPERTIES AFTER APPLICATION		
Drying	Room temperature drying (18-22°C / 64 – 72°F e 65-70% relative humidity) complete drying	12 h
	Dust free	10 min
	Touch dry	20 min
	Hard dry	12 h
	Sandable after (time)	4 h
	Maximum time between layers without sanding	2-3 h
	Hot air drying	(Time and temperature according to the drying system in use)
Shelf life	24 months after production	
SPECIFIC WARNINGS	Being exotic woods of different source and variety, it is recommended to make preliminary tests to determine the coating cycle reliability	



WARNINGS

In a coating process with professional products:

- besides the product quality, the final result also depends on numerous other variables, such as environmental conditions; homogeneity in the quality of the support; the constancy of the application cycle; the plants performance; the proper use of the product, etc.
- in the process of industrial coating a certain waste of product is to be considered normal and therefore not attributable to product quality
- The final colour is influenced by the quality and preparation of the support and the conditions of application, for this reason it is essential to check in advance the result in terms of final use

Our Company cannot ensure the control of the coating process carried out by the user. We cannot, therefore, take on any responsibility for the final result achieved through the use of our products. On the other hand, we guarantee the consistency of the chemical and physical characteristics of the product indicated in the relevant Technical Data Sheet, pledging to replace it if it does not correspond to the declared features. Data on the chemical and physical characteristics of the product are recorded at 20°C / 68°F and 70% R.U.

For best results, the optimum conditions of application are:

- Ambient temperature between 18 and 22°C (64 - 72 °F)
- ambient relative humidity between 65 and 70%
- support humidity between 8 and 14%

The conditions to be observed scrupulously are:

- A solvent-based product should be stored indoors at temperatures not below 0 °C / 32°F or above 35 °C / 95°F, in a properly ventilated place, not exposed to solar radiation
- Always shake the products well before use
- Before use, always shake well the product mixed with any other components such as catalysts, accelerators, thinners
- The application must not take place at a temperature lower than 15 °C / 59°F or above 30°C / 86°F
- The drying should not take place at a temperature below 15 °C / 59°F
- The ambient relative humidity during drying should be between 50% and 70%
- To decant paints, exclusively use containers made of suitable material, such as polyethylene and stainless steel
- After use, we recommend that you always close the can carefully

The end result of the coating cycle is the sole responsibility of the users, who must make sure that the product matches their needs and that environmental conditions, application or media specifications do not require substantial changes of use

It is the user's responsibility:

- Adhere to the conditions indicated above
- comply with the rules of hygiene and safety during product application, according to the descriptions given in the safety data sheets
- for solvent-based products spark-proof equipment should be used
- It is forbidden to smoke while using the product

At the bottom of each sheet there is a date of validity

The Company invites you to check with their staff that the product data sheet in your possession is the most updated, since the characteristics of the products are subject to adjustments over time

For more information, please contact (see below):

Issue date: 2021-03

Rev.: 1